

## Key Features

AMS-S-8802, Type 2, Class B-2  
Bonds Well to Most Substrates  
HMS 16-1985, Compound IV, Class 2  
Resistant to Fuel, Lubricants, Water and Weather  
Room or Elevated Temperature Cure  
User-friendly Packaging

## Uncured

Pot Life 2 hours  
Viscosity Paste  
Shelf Life 6 Months @ < -40°C

## Cure Options

4 hours @ 74°C  
16 hours @ 66°C  
72 hours @ 25°C

## Cured Properties

(Based on cure of 4 hours @ 74°C)

Color	Grey
Shore A Hardness	51
Density (g/cc)	1.6
% Shrinkage Linear	0.3

## Electrical Properties

(Based on cure of 4 hours @ 74°C)

Volume Resistivity (ohm-cm)	2.6E 10 @ 500 VDC
-----------------------------	-------------------

## Product Description:

0148 is a grey, one-component, polysulfide adhesive specifically designed for staking and bonding applications on integral fuel tanks and pressurized cabins. This product can also be used in any area where contact with aircraft fuel, lubricants, oil, water, and weather is common and resistance to those environments is required. 0148 is certified to AMS-S-8802, Type 2, Class B-2 and HMS 16-1985, Compound IV, Class 2 specifications and can be cured at either room or elevated temperatures. This material will bond well to most substrates such as metals (including aluminum, magnesium, titanium, and steel), glass, ceramics, and most plastics and is offered in very user-friendly packaging.

## Thermal Properties

(Based on cure of 4 hours @ 74°C)

Glass Transition Temp (°C)	-50
Degradation Temp. (°C)	250

The data contained herein is provided for informational purposes only and are believed to be reliable. APPLI-TEC does not guarantee suitability of this product for any resultant application or freedom from patent infringement. Furthermore, APPLI-TEC disclaims any liability for incidental and consequential damages of any kind including but not limited to lost profits.

7 Industrial Way, Unit 1, Salem, NH 03079 / Phone: 603-685-0500 / Fax: 603-685-0236 / Web: [www.appli-tec.com](http://www.appli-tec.com)