

Key Features

High Glass Transition Temperature
Low Density
Low Impedance
UV Resistant

Cured Properties

Color	Off-white
Shore D Hardness	83
Glass Transition Temp (°C)	130
Density (g/cc)	0.69

Product Description:

0676 is an off-white, low density, low impedance cast thermoset epoxy material used in acoustic applications. This material is UV resistant and is available as cast blocks as well as machined wafers. It features a high glass transition temperature of 130°C and a low density of 0.69 g/cc.

Thermal Properties

Glass Transition Temp (°C)	130
Degradation Temp. (°C)	>250

Acoustic Properties

Velocity (m/s)	2,369
Impedance (MRayles)	1.622
Loss (dB/cm-MHz)	-6.0
Density (g/cc)	0.69

The data contained herein is provided for informational purposes only and are believed to be reliable. APPLI-TEC does not guarantee suitability of this product for any resultant application or freedom from patent infringement. Furthermore, APPLI-TEC disclaims any liability for incidental and consequential damages of any kind including but not limited to lost profits.