

## 1.26 W/mK

An electrically isolating material, 5308 was designed specifically for underfilling, staking and encapsulating electronics on circuit boards, as well as potting and encapsulating power supplies, transformers, and coils. Featuring a 3-hour pot life, 5308 has good flowability, making it ideal for applications requiring a self-leveling material. The material meets NASA's outgassing requirements, is resistant to solvents and chemicals, and is considered non-hazardous per D.O.T. regulations.

<b>UNCURED</b>	
Pot Life @ 25°C	3 hours
Viscosity @ 25°C	100,000 cPs
Shelf Life @ -40°C	12 Months (Cryo-Pac®)
Shelf Life @ 25°C	12 Months (Appli-Pac®)
Mix Ratio	100A:2.38B Parts By Weight
<b>CURE OPTIONS</b>	2 hours @ 80°C    4 hours @ 60°C
<b>CURED PROPERTIES</b>	Based on cure of 2 hours @ 80°C
Color	Black
Shore D Hardness	90
Glass Transition Temp (°C)	100
Density (g/cc)	2.46
Lap Shear 2024T3 Clad (psi)	2,000
Shrinkage Linear (%)	0.17
<b>CURED PROPERTIES</b>	Based on cure of 4 hours @ 60°C
Shrinkage Linear (%)	0.04
<b>ELECTRICAL PROPERTIES</b>	Based on cure of 2 hours @ 80°C
Dielectric Constant	5.5 @ 100 kHz
Dissipation Factor	0.01 @ 100 kHz
Dielectric Strength (volts/mil)	445
Volume Resistivity (ohm-cm)	4.0E 15 @ 500 VDC
<b>THERMAL PROPERTIES</b>	Based on cure of 2 hours @ 80°C
Glass Transition Temp (°C)	100
Degradation Temp (°C)	300
Thermal Conductivity (W/mK)	1.26
<b>OUTGASSING PROPERTIES</b>	Based on cure of 2 hours @ 80°C
TML (%)	0.12
CVCM (%)	0.01
WVR (%)	0.04
<b>ACOUSTIC PROPERTIES</b>	
Velocity (m/s)	3,124
Impedance (MRayles)	7.69
Loss (dB/cm-MHz)	-7.71
Density (g/cc)	2.46

### KEY FEATURES

D.O.T. Non-Hazardous

Electrically Isolating

High Glass Transition Temperature

High Temperature Resistant

High Thermal Conductivity

Low Shrinkage

Flowable

### Talk to an engineer:

[service@appli-tec.com](mailto:service@appli-tec.com)

603-685-0500 ext. 528

[www.appli-tec.com](http://www.appli-tec.com)

7 Industrial Way, Unit 1, Salem, NH 03079

The data contained herein is provided for informational purposes only and are believed to be reliable. APPLI-TEC does not guarantee suitability of this product for any resultant application or freedom from patent infringement. Furthermore, APPLI-TEC disclaims any liability for incidental and consequential damages of any kind including but not limited to lost profits.

Rev B

9/27/2016