

1.38 W/mK

5316 is a room temperature curing, black, flowable, electrically isolating, thermally conductive epoxy. The material was designed specifically for underfilling, staking and encapsulating electronics on circuit boards as well as potting and encapsulating power supplies, transformers, and coils. 5316 features a long work life and is ideal for applications requiring a self-leveling, thermal conductive epoxy with resistance to solvents and chemicals. 5316 is supplied as a two-part room temperature storage kit. Contact customer service for pre-mixed and frozen options.

UNCURED	
Pot Life @ 25°C	1.5 hours
Viscosity, Mixed @ 25°C	12,500 cPs
Viscosity, Part A @ 25°C	Paste
Viscosity, Part B @ 25°C	250 cPs
Shelf Life @ 25°C	12 Months
Mix Ratio	100A:5.6B Parts By Weight
CURE OPTIONS	24 hours @ 25°C 4 hours @ 65°C
CURED PROPERTIES	Based on cure of 24 hours @ 25°C
Color	Black
Shore D Hardness	85
Glass Transition Temp (°C)	55
Density (g/cc)	2.5
Lap Shear 2024T3 Clad (psi)	2,500
THERMAL PROPERTIES	Based on cure of 24 hours @ 25°C
Glass Transition Temp (°C)	55
Degradation Temp. (°C)	300
Thermal Conductivity (W/mK)	1.38

KEY FEATURES

Electrically Isolating

High Thermal Conductivity

Low Shrinkage

Flowable

Talk to an engineer:

service@appli-tec.com

603-685-0500 ext. 528

www.appli-tec.com

7 Industrial Way, Unit 1, Salem, NH 03079

The data contained herein is provided for informational purposes only and are believed to be reliable. APPLI-TEC does not guarantee suitability of this product for any resultant application or freedom from patent infringement. Furthermore, APPLI-TEC disclaims any liability for incidental and consequential damages of any kind including but not limited to lost profits.

Rev A

10/31/2018