

## 0.25 W/mK

The free-flowing version of our 7800 material, Appli-Thane 7810 is ideal for coating applications. Both 7810 and 7800 are often used together for “dam and fill”: use the higher viscosity 7800 to create the dam, then 7810 to fill in. Appli-Thane 7810 features good flow and wetting, is easily reworkable, and meets NASA’s low outgassing requirements.

<b>UNCURED</b>	
Work Life @ 25°C	1.5 hours
Viscosity @ 25°C	6,400 cPs
Thixotropic Index	1.0
Shelf Life	6 Months @ -40°C    9 Months @ -60°C
<b>CURE OPTIONS</b>	2.5 hours @ 66°C    72 hours @ 25°C
<b>CURED PROPERTIES</b>	Based on cure of 2.5 hours @ 66°C
Color	Clear
Shore A Hardness	65
Glass Transition Temp (°C)	-74
Density (g/cc)	0.96
Lap Shear 2024T3 Clad (psi)	400
Tensile Modulus (psi)	735
Elongation (%)	50
Tensile Strength at Break (psi)	240
Fungus Resistance	Non-nutrient
<b>ELECTRICAL PROPERTIES</b>	Based on cure of 2.5 hours @ 66°C
Dielectric Constant	2.85 @ 1 MHz
Dissipation Factor	0.05 @ 1 MHz
Dielectric Strength (volts/mil)	1,120
Volume Resistivity (ohm-cm)	2.0E 13 @ 500 VDC
Arc Resistance (seconds)	123
<b>THERMAL PROPERTIES</b>	Based on cure of 2.5 hours @ 66°C
CTE below Tg (ppm/°C)	80
CTE above Tg (ppm/°C)	200
Glass Transition Temp (°C)	-74
Operating Temp. Range (°C)	-100 to 125
Thermal Conductivity (W/mK)	0.25
<b>OUTGASSING PROPERTIES</b>	Based on cure of 2.5 hours @ 66°C
TML (%)	0.38
CVCM (%)	0.01
WVR (%)	0.20
<b>ACOUSTIC PROPERTIES</b>	
Velocity (m/s)	1,600
Impedance (MRayles)	1.53
Loss (dB/cm-MHz)	-4.8

### KEY FEATURES

Free Flowing

Electrically Insulative

Flexible

Hydrolytic Stability

Long Pot Life

Low Glass Transition Temperature

Low Modulus

Meets NASA Outgassing Requirements

Solvent Resistant

Fungus Resistant

### Chat with a specialist:

[service@appli-tec.com](mailto:service@appli-tec.com)

603-685-0500 ext. 526

[www.appli-tec.com](http://www.appli-tec.com)

7 Industrial Way, Unit 1, Salem, NH 03079

The data contained herein is provided for informational purposes only and are believed to be reliable. APPLI-TEC does not guarantee suitability of this product for any resultant application or freedom from patent infringement. Furthermore, APPLI-TEC disclaims any liability for incidental and consequential damages of any kind including but not limited to lost profits.

Rev H

3/1/2022

Density (g/cc)

0.96