

Thixotropic consistency keeps material from sagging once applied

0316 is an opaque amber, one-component, precision mixed, degassed, and frozen, electrically isolating, Space Flight Grade, precision mixed and frozen general purpose urethane adhesive. It features a very thixotropic consistency which keeps this material from sagging once applied. This material can be cured at either room or elevated temperatures. 0316 bonds well to most substrates such as metals, glass, ceramics, and plastics and meets NASA outgassing requirements with a TML of 0.61% and a CVCM of <0.01%. The material meets NASA's outgassing requirements.

UNCURED	
Work Life @ 25°C	30 minutes
Pot Life @ 25°C	15 minutes
Viscosity @ 25°C	Paste
Shelf Life	3 weeks @ -40°C 3 months @ -60°C TBD @ -75°C
CURE OPTIONS	8 hours @ 93°C 7 days @ 25°C 24 hours @ 23°C + 16 hours @ 65°C
CURED PROPERTIES	Based on cure of 8 hours @ 93°C
Color	Opaque Amber
Shore A Hardness	70
Glass Transition Temp (°C)	-70
Density (g/cc)	0.97
ELECTRICAL PROPERTIES	Based on cure of 24 hours @ 23°C + 16 hours @ 65°C
Volume Resistivity (ohm-cm)	5.1E 14 @ 500 VDC
THERMAL PROPERTIES	Based on cure of 24 hours @ 23°C + 16 hours @ 65°C
CTE above Tg (ppm/°C)	188
CTE below Tg (ppm/°C)	Not Determined
Glass Transition Temp (°C)	-76
Operating Temp. Range (°C)	-100 to 130
OUTGASSING PROPERTIES	Based on cure of 24 hours @ 23°C + 16 hours @ 65°C
TML (%)	0.61
CVCM (%)	<0.01
WVR (%)	0.06
ACOUSTIC PROPERTIES	
Velocity (m/s)	1,622
Impedance (MRayles)	1.578
Loss (dB/cm-MHz)	-6.7
Density (g/cc)	0.97

KEY FEATURES

Bonds Well to Most Substrates

Electrically Isolating

Very Thixotropic

Room or Elevated Temperature Cure

Space Flight Grade

User-friendly Packaging

Meets NASA Outgassing Requirements

Talk to an engineer:

service@appli-tec.com

603-685-0500 ext. 528

www.appli-tec.com

7 Industrial Way, Unit 1, Salem, NH 03079

The data contained herein is provided for informational purposes only and are believed to be reliable. APPLI-TEC does not guarantee suitability of this product for any resultant application or freedom from patent infringement. Furthermore, APPLI-TEC disclaims any liability for incidental and consequential damages of any kind including but not limited to lost profits.

Rev D

1/29/2016