

UNCURED	
Work Life	120 hours
Shelf Life	14 days @ < 20°C 6 months @ < 0°C 12 months @ < -18°C
CURE OPTIONS	30 minutes @ 150°C 2 hours @ 125°C 4 hours @ 115°C
CURED PROPERTIES	
Color	Amber
Lap Shear 2024T3 Clad FPL Etch (psi)	4,300 @ 25°C
Specific Gravity	1.20
ELECTRICAL PROPERTIES	
Volume Resistivity (ohm*cm)	1.0E + 14
THERMAL PROPERTIES	
CTE (10 ⁻⁶ /°C) above T _g	440
CTE (10 ⁻⁶ /°C) below T _g	85
Glass Transition Temp (°C)	120

KEY FEATURES

Electrically Isolating

High Glass Transition Temperature

High Shear Strength

Thickness: 0.0015"

Talk to an engineer:

service@appli-tec.com

603-685-0500 ext. 528

www.appli-tec.com

7 Industrial Way, Unit 1, Salem, NH 03079

The data contained herein is provided for informational purposes only and are believed to be reliable. APPLI-TEC does not guarantee suitability of this product for any resultant application or freedom from patent infringement. Furthermore, APPLI-TEC disclaims any liability for incidental and consequential damages of any kind including but not limited to lost profits.

Rev D

12/7/2011