

A non-tested supported epoxy film.

UNCURED	
Work Life (hr)	120
Shelf Life	5 days @ < 32°C 6 months @ < -18°C
CURE OPTIONS	
	1.5 hours @ 121° C
CURED PROPERTIES	
Bell Peel Strength (lbf/in)	80 @ 25°C (ASTM-D 3167)
Color	Purple
Lap Shear 2024T3 Clad FPL Etch (psi)	2,000 @ 121°C 3,700 @ 82°C 5,000 @ 25°C
THERMAL PROPERTIES	
Glass Transition Temp (°C)	110

KEY FEATURES

High Bell Peel Strength

High Elevated Temperature Strength

High Shear Strength

Thickness: 0.012"

Chat with a specialist:

service@appli-tec.com

603-685-0500 ext. 526

www.appli-tec.com

7 Industrial Way, Unit 1, Salem, NH 03079

The data contained herein is provided for informational purposes only and are believed to be reliable. APPLI-TEC does not guarantee suitability of this product for any resultant application or freedom from patent infringement. Furthermore, APPLI-TEC disclaims any liability for incidental and consequential damages of any kind including but not limited to lost profits.

Rev F

3/1/2022