

<b>UNCURED</b>			
Work Life (hr)	120		
Shelf Life	5 days @ < 32°C    6 months @ < -18°C		
<b>CURE OPTIONS</b>	1.5 hours @ 121° C		
<b>CURED PROPERTIES</b>			
Bell Peel Strength (lbf/in)	80 @ 25°C (ASTM-D 3167)		
Color	Purple		
Lap Shear 2024T3 Clad FPL Etch (psi)	2,000 @ 121°C	3,700 @ 82°C	5,000 @ 25°C
<b>THERMAL PROPERTIES</b>			
Glass Transition Temp (°C)	110		

**KEY FEATURES**

High Bell Peel Strength

High Elevated Temperature Strength

High Shear Strength

Thickness: 0.012"

**Talk to an engineer:**

[service@appli-tec.com](mailto:service@appli-tec.com)

603-685-0500 ext. 528

[www.appli-tec.com](http://www.appli-tec.com)

7 Industrial Way, Unit 1, Salem, NH 03079

The data contained herein is provided for informational purposes only and are believed to be reliable. APPLI-TEC does not guarantee suitability of this product for any resultant application or freedom from patent infringement. Furthermore, APPLI-TEC disclaims any liability for incidental and consequential damages of any kind including but not limited to lost profits.

Rev E

12/7/2011