

Excellent choice for bonding dissimilar substrates and assemblies requiring thick bond lines

5018 is an amber, electrically isolating, toughened, precision mixed, degassed, and frozen epoxy. It features excellent low temperature properties, a long work life of 6 hours, and a low viscosity making it a very user-friendly epoxy. Once cured this material is tough and flexible making this product an excellent choice for bonding dissimilar substrates and assemblies requiring thick bond lines. 5018 will bond well to most substrates such as metals, glass, ceramics, and most plastics. This material has a CVCM of 0.18% which exceeds the 0.10% limit for low outgassing. The TML is 0.75% which does pass low outgassing

UNCURED	
Work Life @ 25°C	6 hours
Viscosity @ 25°C	3,500 cPs
Pot Life @ 25°C	3 hours
Shelf Life	12 months @ -40°C 24 months @ -60°C
CURE OPTIONS	7 days @ 25°C 72 hours @ 45°C 6 hours @ 80°C
CURED PROPERTIES	Based on cure of 6 hours @ 80°C
Color	Amber
Shore D Hardness	80
Glass Transition Temp (°C)	60
Density (g/cc)	1.13
ELECTRICAL PROPERTIES	Based on cure of 6 hours @ 80°C
Volume Resistivity (ohm-cm)	1.0E 14 @ 500 VDC
THERMAL PROPERTIES	Based on cure of 6 hours @ 80°C
Glass Transition Temp (°C)	60
Degradation Temp. (°C)	>240
ACOUSTIC PROPERTIES	
Velocity (m/s)	2,421
Impedance (MRayles)	2.736
Loss (dB/cm-MHz)	-6.9
Density (g/cc)	1.13

KEY FEATURES

Bonds Well to Most Substrates

Long Work Life

Low Viscosity

High Bond Strength

Thermal Shock Resistant

User-friendly Packaging

Chat with a specialist:

service@appli-tec.com

603-685-0500 ext. 526

www.appli-tec.com

7 Industrial Way, Unit 1, Salem, NH 03079

The data contained herein is provided for informational purposes only and are believed to be reliable. APPLI-TEC does not guarantee suitability of this product for any resultant application or freedom from patent infringement. Furthermore, APPLI-TEC disclaims any liability for incidental and consequential damages of any kind including but not limited to lost profits.