

## UV cure for high strength bonds

6007 is a 100% solids, electrically isolating, heat curable UV acrylate, precision mixed, degassed, and frozen adhesive that is ideal for fiber optic applications. This material is free flowing and changes color from amber to red when cured. 6007 features a deep UV cure which will form high strength bonds to most substrates such as metals, ceramic, glass, and most plastics and will finish curing with the application of heat. This cure method is excellent when rapid de-fixturing is required. This adhesive passes the NASA outgassing requirements.

<b>UNCURED</b>	
Pot Life @ 25°C	18 hours
Viscosity @ 25°C	1,300 cPs
Color	Amber
Shelf Life	6 weeks @ -18°C    12 months @ -40°C
<b>CURE OPTIONS</b>	3 J/cm <sup>2</sup> + 30 minutes @ 120°C 3 J/cm <sup>2</sup> + 2 hours @ 96°C
<b>CURED PROPERTIES</b>	Based on cure of 3 J/cm <sup>2</sup> + 30 minutes @ 120°C
Color	Red
Shore D Hardness	85
Glass Transition Temp (°C)	135
Density (g/cc)	1.1
Lap Shear 2024T3 Clad (psi)	2,300
<b>THERMAL PROPERTIES</b>	Based on cure of 3 J/cm <sup>2</sup> + 30 minutes @ 120°C
Glass Transition Temp (°C)	135
<b>OUTGASSING PROPERTIES</b>	Based on cure of 3 J/cm <sup>2</sup> + 30 minutes @ 120°C
TML (%)	0.38
CVCM (%)	0.01
WVR (%)	0.24

### KEY FEATURES

Bonds Well To Most Substrates

Deep UV Cure

Free Flowing

Full Shadow Cure With Heat

Ideal For Fiber Optic Applications

Meets NASA Outgassing Requirements

Changes Color Once Cured

✓ RoHS Compliant

### Chat with a specialist:

[service@appli-tec.com](mailto:service@appli-tec.com)

603-685-0500 ext. 526

[www.appli-tec.com](http://www.appli-tec.com)

7 Industrial Way, Unit 1, Salem, NH 03079

The data contained herein is provided for informational purposes only and are believed to be reliable. APPLI-TEC does not guarantee suitability of this product for any resultant application or freedom from patent infringement. Furthermore, APPLI-TEC disclaims any liability for incidental and consequential damages of any kind including but not limited to lost profits.

Rev J

7/10/2024