

## 24 hour work life

6207 is a gray, one-component, UV/heat dual cure, precision mixed, degassed, and frozen acrylate adhesive that bonds well to most substrates (metals, ceramic, glass, and most plastics). It has the capabilities of both a deep UV cure and full shadow cure with heat and is ideal for fiber optic applications. It is a free-flowing material with a long work life, able to be dispensed up to 24 hours after thaw. 6207 can be tacked with UV, removed from the fixture, and post cured with heat later in the assembly process. It offers a low coefficient of thermal expansion to minimize part movement during thermal cycling.

<b>UNCURED</b>	
Work Life @ 25°C	24 hours
Viscosity @ 23°C	35,000 cPs
Shelf Life @ -40°C	12 months
<b>CURE OPTIONS</b>	Based on cure of 6,000 mJ + 30 minutes @ 120°C
<b>CURED PROPERTIES</b>	Based on cure of 6,000 mJ + 30 minutes @ 120°C
Color	Gray
Shore D Hardness	94
Glass Transition Temp (°C)	125
Density (g/cc)	1.6
Lap Shear 2024T3 Clad (psi)	1,500
<b>ELECTRICAL PROPERTIES</b>	Based on cure of 6,000 mJ + 30 minutes @ 120°C
Volume Resistivity (ohm-cm)	1.0E 12 @ 500 VDC
<b>THERMAL PROPERTIES</b>	Based on cure of 6,000 mJ + 30 minutes @ 120°C
CTE below Tg (ppm/°C)	43
CTE above Tg (ppm/°C)	98
Glass Transition Temp (°C)	125
<b>OUTGASSING PROPERTIES</b>	Based on cure of 6,000 mJ + 30 minutes @ 120°C
TML (%)	0.32
CVCM (%)	<0.01
WVR (%)	0.16
<b>ACOUSTIC PROPERTIES</b>	
Velocity (m/s)	3,035
Impedance (MRayles)	4.98
Loss (dB/cm-MHz)	-5.05
Density (g/cc)	1.6

### KEY FEATURES

Bonds Well to Most Substrates

Deep UV Cure

Full Shadow Cure with Heat

Ideal for Fiber Optic Applications

Long Pot Life

Fast Tack Minimizes Fixture Costs

Secondary Cure after Removal from Fixture

### Chat with a specialist:

[service@appli-tec.com](mailto:service@appli-tec.com)

603-685-0500 ext. 526

[www.appli-tec.com](http://www.appli-tec.com)

7 Industrial Way, Unit 1, Salem, NH 03079

The data contained herein is provided for informational purposes only and are believed to be reliable. APPLI-TEC does not guarantee suitability of this product for any resultant application or freedom from patent infringement. Furthermore, APPLI-TEC disclaims any liability for incidental and consequential damages of any kind including but not limited to lost profits.

Rev M

1/31/2022