

0.3 W/mK

This thixotropic, easily reworkable aerospace urethane is ideal for bonding and staking applications where thermal conductivity isn't required. The material features a room temperature cure while also meeting NASA's low outgassing requirements. With low modulus and low Tg, 7800 is a suitable substitute for many silicones in electronic applications.

UNCURED	
Work Life @ 25°C	1.5 hours
Viscosity @ 25°C	45,000 cPs
Thixotropic Index	3.0
Shelf Life @ -40°C	6 Months @ -40°C 9 Months @ -40°C
CURE OPTIONS	2.5 hours @ 66°C 7 days @ 25°C
CURED PROPERTIES	Based on cure of 2.5 hours @ 66°C
Color	Translucent
Shore A Hardness	65
Glass Transition Temp (°C)	-74
Density (g/cc)	1.0
Lap Shear 2024T3 Clad (psi)	500
Tensile Strength (psi)	625
Tensile Modulus (psi)	400
Elongation (%)	90
Fungus Resistance	Non-nutrient
Chloride Ion Concentration, ppm	26.7
ELECTRICAL PROPERTIES	Based on cure of 2.5 hours @ 66°C
Dielectric Constant	3.5 @ 10 kHz 3.1 @ 100 kHz 2.9 @ 1 MHz
Dissipation Factor	0.08 @ 10 kHz 0.06 @ 100 kHz 0.05 @ 1 MHz
Dielectric Strength (volts/mil)	1,220
Volume Resistivity (ohm-cm)	2.2E 13 @ 500 VDC
THERMAL PROPERTIES	Based on cure of 2.5 hours @ 66°C

KEY FEATURES

Thixotropic

Electrically Insulative

Flexible

Hydrolytic Stability

Long Pot Life

Low Glass Transition Temperature

Low Modulus

Meets NASA Outgassing Requirements

Solvent Resistant

Fungus Resistant

Talk to an engineer:

service@appli-tec.com

603-685-0500 ext. 528

www.appli-tec.com

7 Industrial Way, Unit 1, Salem, NH 03079

The data contained herein is provided for informational purposes only and are believed to be reliable. APPLI-TEC does not guarantee suitability of this product for any resultant application or freedom from patent infringement. Furthermore, APPLI-TEC disclaims any liability for incidental and consequential damages of any kind including but not limited to lost profits.

Rev F

8/24/2020

CTE below Tg (ppm/°C)	80
CTE above Tg (ppm/°C)	200
Glass Transition Temp (°C)	-74
Operating Temp. Range (°C)	-100 to 125
Thermal Conductivity (W/mK)	0.3
OUTGASSING PROPERTIES Based on cure of 2.5 hours @ 66°C	
TML (%)	0.43
CVCM (%)	0.01
WVR (%)	0.17
ACOUSTIC PROPERTIES	
Velocity (m/s)	1,616
Impedance (MRayles)	1.60
Loss (dB/cm-MHz)	-6.9
Density (g/cc)	1.0