

## A low viscosity, flowable epoxy

5336 is a black, electrically isolating, thermally conductive epoxy designed specifically for staking and encapsulating electronics on circuit boards as well as potting and encapsulating power supplies, transformers, and coils. This material is ideal for applications requiring a thermally conductive epoxy with resistance to solvents and chemicals. 5336 is supplied in frozen syringes or as a two-part, room temperature kit.

<b>UNCURED</b>	
Pot Life @ 25°C	1.5 hours
Viscosity, Mixed, @ 25°C	39,500 cPs
Shelf Life	12 months @ -60°C    6 months @ -40°C 12 months @ 25°C
Mix Ratio 100A	6B Parts by Weight
<b>CURE OPTIONS</b>	2 hours @ 80°C    4 hours @ 60°C 24 hours @ 25°C
<b>CURED PROPERTIES</b>	Based on cure of 2 hours @ 80°C
Color	Black
Shore D Hardness	93
Glass Transition Temp (°C)	63
Density (g/cc)	2.5
Lap Shear (psi)	2040
<b>ELECTRICAL PROPERTIES</b>	Based on cure of 2 hours @ 80°C
Dielectric Constant	5.99 @ 100 kHz
Dissipation Factor	0.14 @ 100 kHz
Dielectric Strength (volts/mil)	478
Volume Resistivity (ohm-cm)	3.5E+15 @ 500 VDC
<b>THERMAL PROPERTIES</b>	Based on cure of 2 hours @ 80°C
Glass Transition Temp (°C)	63
Degradation Temp. (°C)	300
Thermal Conductivity (W/mK)	1.48
<b>OUTGASSING PROPERTIES</b>	Based on cure of 2 hours @ 80°C
TML (%)	0.31
CVCM (%)	0.01
WVR (%)	0.04

### KEY FEATURES

- Electrically Isolating
- High Thermal Conductivity
- Low Shrinkage
- Flowable
- Low Outgassing

### Chat with a specialist:

[service@appli-tec.com](mailto:service@appli-tec.com)

603-685-0500 ext. 526

[www.appli-tec.com](http://www.appli-tec.com)

7 Industrial Way, Unit 1, Salem, NH 03079

The data contained herein is provided for informational purposes only and are believed to be reliable. APPLI-TEC does not guarantee suitability of this product for any resultant application or freedom from patent infringement. Furthermore, APPLI-TEC disclaims any liability for incidental and consequential damages of any kind including but not limited to lost profits.

Rev F

8-29-2022